

Electromagnetic properties of a Fermi liquid superconductor with singular Landau parameter $F_{1s} \rightarrow -1$

Tai-Kai Ng

*Department of Physics, Hong Kong University of Science and Technology,
Clear Water Bay Road, Kowloon, Hong Kong*

(Dated: February 5, 2008)

Abstract

The electromagnetic properties of a Fermi liquid superconductor with singular Landau parameter $F_{1s} \rightarrow -1$, corresponding to a state with marginal spin-charge separation (MSCS) is analyzed in this paper. We show that the MSCS state describes a strongly phase-disordered superconductor which is a diamagnetic metal with Drude-like optical conductivity. The phase diagram and electromagnetic properties of the MSCS state is found to be in qualitative agreement with what is observed in the pseudo-gap phase of (underdoped) High- T_c cuprates. We predicted that vortices with *un-quantized* magnetic flux will be observed in the pseudo-gap phase.

The understanding of the normal state of underdoped cuprates (pseudo-gap phase) remains one of the major theoretical challenge to the condensed matter physics community nowadays because the phase seems to violate a number of properties required by Fermi liquid theory^{1,2,3}. On the other hand, the superconducting phase, which is just below the pseudo-gap phase in the $T - \delta$ (δ = hole concentration) phase diagram, seems to obey Fermi-liquid (superconductor) phenomenology pretty well^{1,2,3,4,5}. The proximity of the two phases suggests that it may be possible to describe the pseudo-gap phase starting from an effective Fermi-liquid theory that describes the superconducting state of the cuprates. This scenario, if correct, implies that we may be able to develop an unified phenomenological framework to understand both the pseudo-gap and superconducting phases in underdoped cuprates.

Recently, based on an analysis of the slave-boson mean-field theory (SBMFT) of $t - J$ model, we proposed that the pseudo-gap state can be described as a Fermi liquid superconductor with singular Landau parameter $F_{1s} \rightarrow -1$, corresponding to a state with spin-charge separation in the long wave-length, low frequency limit⁶. We shall call this state a marginally-spin-charge separated state (MSCS) in the following. Superfluidity disappears in the MSCS state because quasi-particles do not carry current in this limit⁶. In this paper we shall examine the electromagnetic properties of the MSCS state in more details by considering a general Landau Fermi liquid superconductor with Fermi liquid parameter $F_{1s} \rightarrow -1$, but with other Fermi-liquid parameters remaining regular. We shall show that the MSCS state describes a strongly phase-disordered superconductor which is a diamagnetic metal with Drude-like optical conductivity. A prediction on the appearance of vortices with un-quantized magnetic flux is made.

In the MSCS scenario, the pseudo-gap phase is a Fermi-liquid superconductor with a parent BCS superconductor mean-field transition temperature $T_M \sim T^*$ (pseudo-gap temperature). The current carried by quasi-particles are renormalized by the Landau parameter $1 + F_{1s}$ ^{2,3,4,5} and vanishes in limit $F_{1s} \rightarrow -1$ ⁶. We shall consider in the following a d -wave superconductor with Landau parameter $1 + F_{1s}(T) = z > 0$ at temperature $T = 0$ and reduced gradually to $1 + F_{1s}(T) \rightarrow 0$ at $T = T_c < T_M$. We note that translational and rotational symmetries are strongly broken by the Fermi surface geometry in cuprates, and the Landau interactions $F_{\vec{k}\vec{k}}^{s(a)}$ depend in general not only on the relative angle between $\vec{k}$ and $\vec{k}'$, but also on the directions of the $\vec{k}$ and $\vec{k}'$ vectors themselves⁷. This is not taken into account in our simply parametrization of Landau parameter since the aim of our paper

is not to establish a complete Fermi liquid theory for cuprates, but to examine the general consequences of $F_{1s} \rightarrow -1$. We note also that there exists no general relation between the effective mass m^*/m and F_{1s} for a system with broken translational symmetry⁷. For an ordinary (non-superconducting) Fermi liquid which breaks translational symmetry, the point $F_{1s} = -1$ is a critical point⁷ separating the Fermi liquid state ($F_{1s} > -1$) and a state with spontaneous current ($F_{1s} < -1$) and magnetic flux. However, for a Fermi liquid superconductor, this instability is suppressed by the opening of gap on the Fermi surface.

When $F_{1s} \rightarrow -1$, we have to include finite wave-vector and frequency corrections to the Landau interaction and replaces F_{1s} by a Landau function $F_{1s}(q, \omega)$. Assuming that $F_{1s}(q, \omega)$ is regular at $q, \omega \rightarrow 0$, we expect $F_{1s}(q, \omega) \sim -1 + \chi_d(T)q^2 + K(\omega)$ in the limit $q \ll k_F, \hbar\omega \ll T_M$, where $\chi_d(T) > 0$ (stability requirement for Fermi liquids) and $K(\omega)$ are phenomenological parameter and function to be determined. We shall see later that $\chi_d(T)$ measures the magnetic susceptibility of the system and $\chi_d > 0$ implies that the system is diamagnetic. In particular, at $T \rightarrow T_c^+$ we expect

$$\chi_d(T) \sim z \frac{r_M^2}{(T/T_c - 1)^\nu}, \quad (1)$$

where $\nu > 0$ and r_M is a characteristic length scale above which spin-charge separation occurs. Physically the (diamagnetic) susceptibility should diverge as the system approach the superconducting state. We shall assume also that $K(\omega)$ has the form

$$Re\{K(\omega)\} = z \left(\frac{\omega^2}{\omega^2 + \Gamma(T)^2} \right), \quad (2)$$

so that $1 + F_{1s} \rightarrow 0$ at $\omega \rightarrow 0$, and $\rightarrow z$ at $\omega \gg \Gamma(T)$, i.e. the quasi-particles "recover" their charges at $\omega \gg \Gamma(T)$. We shall see later that the recovery of charges at large ω is "required" by the f -sum rule. Notice that

$$Im\{K(\omega)\} = -\frac{z\Gamma(T)\omega}{\omega^2 + \Gamma(T)^2} \neq 0, \quad (3)$$

by the Kramers-Kronig relation. T_M, T_c, z, ν, r_M and $\Gamma(T)$ are phenomenological parameters to be determined from experimental datas on the underdoped cuprates. We shall assume $T_M \gg T_c \sim \delta$ in the following analysis.

Our simple phenomenology has some non-trivial consequences. To see that we examine the current-current response function in the MSCS state. The (transverse) current-current response function $\chi_T(q, \omega; T)$ at temperature T for a Fermi-liquid superconductor is given

by^{6,8}

$$\chi_T(q, \omega; T) = \frac{\chi_{0t}(q, \omega; T)}{1 - \left(\frac{F_{1s}(q, \omega)}{1 + F_{1s}(q, \omega)} \right) \frac{\chi_{0t}(q, \omega; T)}{\chi_{0t}(0, 0; 0)}},$$

where $\chi_{0t}(q, \omega; T)$ is the transverse current-current response function of the corresponding BCS superconductor in the absence of Landau interactions. Using our phenomenological form of $F_{1s}(q, \omega)$, we obtain at small q and $(\omega, k_B T) \ll k_B T_M$,

$$\chi_T(q, \omega; T > T_c) \rightarrow (\chi_d(T)q^2 + K(\omega)) \chi_{0t}(0, 0; 0) + O\left(\frac{T}{T_M}, \frac{\hbar\omega}{k_B T_M}\right), \quad (4)$$

where the $O(\frac{T}{T_M}, \frac{\hbar\omega}{k_B T_M})$ terms are contributions from quasi-particle excitations. At $\omega, T \ll T_M$, the quasi-particle contributions can be neglected and we find that the MSCS state is a diamagnetic metal with magnetic susceptibility $-\chi_d(T)$ and AC conductivity

$$\sigma_d(\omega) \sim \frac{K(\omega)\chi_{0t}(0, 0; 0)}{(-i\omega)} = \frac{z\chi_{0t}(0, 0; 0)}{\Gamma(T) - i\omega}, \quad (5)$$

corresponding to a Drude metal with carrier density $\sim z$ and inverse life time $\Gamma(T)$. Notice that there is no "quasi-particle" contribution to the AC conductivity in our approximation.

This rather surprising result can be better understood by examining the integral

$$I = 2 \int_0^\infty \frac{d\omega}{\pi} \text{Re}[\sigma(\omega)] d\omega,$$

which, according to the f -sum-rule⁷, is a number depending on the total charge density only and is independent of whether the system is in the superconducting or normal state. In the superconducting state at $T = 0$, $I = I_s + I_Q$ where $I_s = (1 + F_{1s})\chi_{0t}(0, 0; 0) = z\chi_{0t}(0, 0; 0)$ is the superfluid contribution to I ^{8,9}. I_Q is the contribution from quasi-particle excitations. Assuming $T \ll T_M$, $\hbar\Gamma(T) \ll k_B T_M$ and the vanishing of superfluidity is driven by $F_{1s} \rightarrow -1$ with the quasi-particle contributions I_Q remaining more or less unaltered, we obtain approximately from Eq. (5)

$$\frac{I_s}{\chi_{0t}(0, 0; 0)} \sim 2 \int_0^\infty \frac{d\omega}{\pi} \frac{\text{Re}[\sigma_d(\omega)]}{\chi_{0t}(0, 0; 0)} = 2 \int_0^\infty \frac{d\omega}{\pi} \frac{\text{Im}[K(\omega)]}{0 - \omega} = (\text{Re}[K(\infty)] - \text{Re}[K(0)]), \quad (6)$$

which says that the missing spectral weight when the system goes from the superconducting state to the pseudo-gap state should "re-appear" in the difference between $K(\infty)$ and $K(0)$ in order to satisfy the f -sum rule. In the MSCS state where $1 + F_{1s}(0, 0) = 0$, we must have $1 + F_{1s}(0, \infty) \rightarrow z$. This is precisely what we have chosen in our phenomenological form of $K(\omega)$. A corresponding contribution to AC conductivity appears indicating that

additional charge degree of freedom not accountable by quasi-particle excitations has to appear in the MSCS state because of charge conservation, i.e. spin-charge separation. The precise form of $K(\omega)$ is determined by the microscopic dynamics of this "anomalous" charge field which cannot be determined by our simple Fermi-liquid phenomenology⁶. Nevertheless analyticity suggests that a Drude-like conductivity is likely to occur, as indicated by our simply parametrization of $K(\omega)$.

To study in more details the properties of the system we derive the Ginzburg-Landau (GL) free energy for the MSCS state. Following Ref.¹⁰, we consider a Fermi-liquid superconductor with Landau parameters F_{0s} and F_{1s} only. Writing the superconductor order parameter ψ in terms of amplitude and phase variables $\psi = \sqrt{\rho}e^{i\theta}$, it was found that the GL free energy at $T \ll T_M$ is¹⁰

$$F_{GL} \sim \int d^d x \left(\frac{\hbar^2}{2m^*} (\nabla \sqrt{\rho})^2 - \alpha(T)\rho + \frac{\bar{\beta}}{2}\rho^2 + \frac{\hbar^2}{2m^*} (1 + F_{1s})\rho (\nabla\theta - \frac{2\pi}{\Phi_0}\vec{A})^2 + \frac{\vec{B}^2}{8\pi} - \frac{\vec{B} \cdot \vec{H}}{4\pi} \right). \quad (7)$$

where $\bar{\beta} = (1 + F_{0s})\beta$. $\alpha(T)$ and β are the usual parameters parameterizing the GL free energy of the BCS superconductor without Landau interactions. $\vec{A}$ is the vector potential, $\vec{B} = \nabla \times \vec{A}$ is the total magnetic field and $\Phi_0 = hc/2e$ is the fluxoid quantum. $\vec{H}$ is the external magnetic field. F_{0s} and F_{1s} appear in the renormalized parameter $\bar{\beta} = (1 + F_{0s})\beta$ and superfluid density $\rho_s = (1 + F_{1s})\rho$, in agreement with Fermi liquid theory^{8,10}. The (mean-field) MSCS state is obtained by replacing $1 + F_{1s} \sim z$ at $T = 0$ by $1 + F_{1s} \sim -\chi_d \nabla^2$ at $T > T_c$ with correspondingly,

$$(1 + F_{1s})\rho (\nabla\theta - \frac{2\pi}{\Phi_0}\vec{A})^2 \rightarrow \chi_d \rho \left((\nabla^2\theta)^2 + 4\pi^2 (\vec{\kappa} - \frac{\vec{B}}{\Phi_0})^2 \right),$$

where $\vec{\kappa} = \frac{1}{2\pi} \nabla \times \nabla\theta$ is the vorticity. Notice the vanishing of superfluid rigidity and disappearance of Meissner effect in the MSCS state. We note also that the resistive response to electric field will be recovered if we consider the time-dependent GL action¹⁰ with finite frequency responses included in F_{1s} .

At $T \ll T_M$, amplitude fluctuations of the superconducting order parameter is unimportant and we can replace the GL free energy by an effective phase free energy

$$F_\theta = \int d^d x \left(\frac{\hbar^2 \bar{\rho} \chi_d}{2m^*} [(\nabla^2\theta)^2 + 4\pi^2 (\vec{\kappa} - \frac{\vec{B}}{\Phi_0})^2] - \frac{\vec{B}^2}{8\pi} - \frac{\vec{B} \cdot \vec{H}}{4\pi} + \frac{\epsilon_v}{2\pi \xi^2} [\vec{\kappa}]^2 \right), \quad (8)$$

where $\bar{\rho} = \alpha(T)/\bar{\beta}$, ϵ_v is the vortex core energy and ξ is the coherence length. Notice that although Meissner effect disappears, a residual interaction between vortices and magnetic field still exists which is proportional to $\chi_d(T)$. Minimizing the free energy with respect to $\vec{B}$, we find that a vortex still bind a total magnetic flux

$$\Phi_v \sim \frac{(\chi_d(T)\lambda^{-2})}{1 + (\chi_d(T)\lambda^{-2})}\Phi_0, \quad (9)$$

where λ is the London penetration depth of the parent BCS superconductor in the absence of Landau interaction. The total vortex energy in the presence of external field $\vec{H}$ is

$$\bar{\epsilon}_{vs}(H) = \epsilon_v \left(1 + \left(\frac{a'\chi_d(T)\xi^{-2}}{1 + (\chi_d(T)\lambda^{-2})} \right) \left(1 - \frac{2Hs}{h_{c2}} \right) \right), \quad (10)$$

where $s = \pm 1$ is the sign of the vorticity and $h_{c2} \sim \Phi_0/2\pi\xi^2$ is the upper critical field for the parent BCS superconductor. a' is an numerical factor of order $O(1)$. The absence of long-range interaction between vortices suggest that the MSCS state is a strongly disordered vortex liquid, with vortex density $n_s(T) \sim \xi^{-2} \exp\left(-\frac{\bar{\epsilon}_{vs}(H)}{k_B T}\right)^{2,11,12}$. Notice that the above estimates become inaccurate at the critical point $T \sim T_c$ when $\chi_d(T)n_s(T) \geq 1$ (see Eq.1)).

The phase diagram of the system can be determined if we assume that $1 + F_{1s} = a(1 - T/T_c)$ at $T < T_c$, where $a \sim z$ and the free energy is given by the usual $x - y$ model phase action^{11,12}

$$F(T < T_c) \sim a \left(1 - \frac{T}{T_c} \right) \frac{\bar{\rho}\hbar^2}{2m^*} \int d^d x \left(\nabla\theta - \frac{2\pi}{\Phi_0} \vec{A} \right)^2. \quad (11)$$

Assuming that the system is quasi-two dimensional we expect that superconductivity will exist at $T < T_{KT} \sim \gamma T_c$, where T_{KT} is the Berezinskii-Kosterlitz-Thouless (BKT) transition^{11,12} temperature and $\gamma \sim \frac{(a\bar{\rho}\hbar^2/4m^*T_c)}{(1+(a\bar{\rho}\hbar^2/4m^*T_c))} < 1$. The system goes through a BKT transition at T_{KT} into the vortex liquid state which is a normal metal with strong superconductivity fluctuations and para-conductivity behavior¹³. This region can be identified with the region with strong Nernst signal in the underdoped cuprates^{14,15}. The system crosses into the MSCS state at $T \geq T_c$ where phase rigidity is lost completely. Notice that the mean-field superconducting-to-MSCS transition is superseded and smeared out by the BKT transition into a crossover. Vortex properties in the MSCS state is anomalous. The magnetic flux trapped in the vortex core is *un-quantized* and decreases gradually when the system crossover to the MSCS state (Eq. (9)).

We next discuss briefly transport properties in the MSCS state. we find that the total electrical conductivity σ of the system is given by the Ioffe-Larkin composition rule¹⁶

$\sigma^{-1} = \sigma_d^{-1} + \sigma_f^{-1}$, where σ_d is the anomalous (Drude) conductivity and $\sigma_f = \sigma_v + \sigma_Q$ is the conductivity from the "Fermi liquid" component. σ_Q is the contribution from excited quasi-particles whereas σ_v is the vortex (superfluid) contribution. Vortex contributions to transport can be determined if we assume that vortex dynamics is the same as vortex dynamics in usual superconductors^{9,13} except that the magnetic flux trapped inside the vortex core is Φ_v . Notice that this assumption implies that transport in the vortex liquid state at $T < T_c$ crossover smoothly to the MSCS state at $T > T_c$. With this assumption the two equations governing vortex dynamics are

$$\begin{aligned}\eta \vec{v}_s + \eta_M s \hat{z} \times \vec{v}_s &= \vec{j} \times \frac{s \Phi_v \hat{z}}{c} - \left(\frac{\partial f_s}{\partial T} \right) \nabla T, \\ \vec{E} &= \frac{\Phi_0 \hat{z}}{c} \times (n_+ \vec{v}_+ - n_- \vec{v}_-)\end{aligned}\tag{12}$$

where $\vec{v}_s$ is the velocity of a vortex with vorticity s , f_s is the free energy associated with a vortex. η is a viscous damping coefficient and η_M is the Magnus parameter. $\vec{j}$ is the electric current and $\vec{E}$ is the electric field induced by vortices motion. The magnetic field is along $+\hat{z}$ direction. Notice that the second equation, which is the Josephson relation, represents phase slip processes⁹ when a vortex pass through a line in space and is not affected by the actual amount of magnetic flux trapped in vortex core.

Solving the equations it is easy to show that vortices contribution to transports are important only when the coupling between vortices and external magnetic field $\sim \chi_d(T)$ is large, and decreases rapidly when $T \gg T_c$. Therefore for $T_M \gg T_c$ we expect that σ_f is dominated by σ_v at low temperature regime $T \sim T_c$, and crossovers to a regime dominated by quasi-particle contributions σ_Q when $T \gg T_c$. In the following we shall examine the low temperature regime where σ_Q is negligible.

Assuming a Bardeen-Stephen type model¹⁷ for η with $\eta \gg \eta_M$, we obtain for the ($\vec{B} = 0$) total resistivity and Nernst signal ($e_N = |\vec{E}|/|\nabla T|$)

$$\begin{aligned}\sigma^{-1} &= \sigma_d^{-1} (1 + b' (\xi^2 N_+(T)) \frac{\Phi_v}{\Phi_0}), \\ e_N &= \frac{2e}{h} \left(\frac{\partial f_s}{\partial T} \right) (\xi^2 N_-(T)) \sigma_d^{-1} + e_{Nd}.\end{aligned}\tag{13}$$

where b' is a numerical factor of order $O(1)$ and $N_{\pm}(T) = n_+(T) \pm n_-(T)$. e_{Nd} is the contribution to Nernst signal from the anomalous charge dynamics which we cannot determine without additional assumptions. For the same reason we cannot determine with

certainty σ_{xy} . Notice that vortex contribution to conductivity and Nernst signal decreases when temperature increases. In particular, we find that for $\chi_d(T)\xi^{-2} \ll 1$,

$$e_N \sim \frac{4}{c} \left(\frac{2e}{\hbar} \right)^2 \left(\frac{\partial f_s}{\partial T} \right) \sigma_d^{-1} e^{\frac{-\epsilon_v}{k_B T}} \frac{\chi_d(T)}{k_B T} H + e_{Nd},$$

which suggests that the dominant temperature dependence of e_N/H is proportional to $\chi_d(T)/k_B T$ at the temperature regime $T \sim a \text{ few } k_B T_c$ where the Nernst signal decreases rapidly with temperature, if we assume that e_{Nd} is small and negligible and ϵ_v is of order of $k_B T_c^2$, in qualitative agreement with what is observed experimentally^{14,15} in underdoped cuprates.

Summarizing, we propose in this paper that the pseudo-gap state in underdoped cuprates is a state with marginal spin-charge separation (MSCS). The general properties of the MSCS state, including the appearance of Drude conductivity, the natural appearance of low temperature Nernst regime and high temperature regime where paraconductivity behavior disappears, seem to agree qualitatively with what is observed experimentally although detailed comparison/fitting with experimental data is not made in this paper. An important prediction of the theory is that vortices with *un-quantized* magnetic flux $\Phi_v < \Phi_0$ which decreases gradually with increasing temperature exist in the MSCS state. This prediction can be tested in rings of multiple grain boundary Josephson junction in the pseudo-gap state¹⁹ and provides an unambiguous test to the theory.

A microscopic realization of the MSCS state is the non-Bose-condensed state in the $U(1)$ gauge theory for the $t - J$ model^{5,6}. In this case, the anomalous charge dynamics is described by a charge $q = 1$ complex scalar field. We note that other possibilities exist. For example, the charge dynamics in the spin-charge separated state will be very different in the $SU(2)$ theory¹⁸ for the $t - J$ model. The phenomenology presented here provided a plausible general framework to understand all these theories which predict spin-charge separation. More detailed investigations of properties of the MSCS state and comparison with experiments will be presented in future papers.

Acknowledgments

This work is supported by HKUGC through grants 602705 and CA05/06.SC04.

- ¹ A. Damascelli and Z. Hussain and Z. X. Shen, Rev. Mod. Phys. **75** 473 (2003).
- ² P. A. Lee and N. Nagaosa and X. G. Wen, Rev. Mod. Phys. **78**, 17 (2006).
- ³ J. Orenstein and A.J. Millis, Science **288**, 468(2000).
- ⁴ A.J. Millis, S.M. Girvin, L.B. Ioffe and A.I. Larkin, J. Phys. Chem. Solids **59**, 1742(1998).
- ⁵ T.K. Ng, Phys. Rev. B **69**, 125112(2004).
- ⁶ C.K. Chan and T.K. Ng, Phys. Rev. B **74**, 172503 (2006).
- ⁷ P. Norieres and D. Pines, "The Theory of Quantum Liquids" (Perseus Books/Westview Press, Boulder, CO, 1999).
- ⁸ A.J. Leggett, Phys. Rev. **140**, A1869(1965); A.I. Larkin, Sov. Phys. JETP **14**, 1498(1964).
- ⁹ M. Tinkham, "Introduction to Superconductivity", (2nd, ed, McGraw Hill, New York, 1996).
- ¹⁰ T.K. Ng and W.T. Tse, to appear in J. of Phys. (Cond. Matt).
- ¹¹ V.L. Berezinskii, Zh. Eksp. Teor, Fiz. **61** 1144 (1971); J.M. Kosterlitz and D.J. Thouless, J. Phys. bf C 5, L124 (1972).
- ¹² V.J. Emery and S. Kivelson, *Nature* **374**, 434(1995).
- ¹³ J.C. Campuzano, M. Norman and M. Randeria, in *Physics of Conventional and Unconventional Superconductors*, edited by K.H. Bennemann and J.B. Ketterson (Springer, Berlin 2003)
- ¹⁴ N.P. Ong, Yayu Wang, S. Ono, Y. Ando and S. Uchida, Ann. Phys. (Leipzig) **13**, No.1-2,9-14 (2004).
- ¹⁵ Y. Wang, L. Li, and N. P. Ong, Phys. Rev. B **73**, 024510 (2006).
- ¹⁶ L.B. Ioffe and A.I. Larkin, Phys. Rev. B **39**, 8988 (1988).
- ¹⁷ J. Bardeen and M.J. Stephen, Phys. Rev. **140**, A1197(1965).
- ¹⁸ P.A. Lee, N. Nagaosa, T.K. Ng and X.G. Wen, Phys. Rev. B **57**, 6003(1998).
- ¹⁹ J. R. Kirtley, C. C. Tsuei, V. G. Kogan, J. R. Clem, H. Raffy, and Z. Z. Li, Phys. Rev. B **68**, 214505 (2003). J. R. Kirtley, C. C. Tsuei, A. Ariando, C.J. M. Verwijs, S. Harkema and H. Hilgenkamp, *Nature Physics* **2**, 190 (2006)).